

Ratings

Voltage: 300 V
 Temperature: 80 °C
 Flammability: VW-1, FT1

Conductor

Conductor count: 2
 Gauge: 28 AWG, 0.09 mm²
 Material: tinned copper strands
 Stranding: $\varnothing 0.127 \times 7$
 Resistance at 20 °C: 240 ohm/km maximum

Insulator

Material: SRPVC, 80 °C
 Color: black, red
 Outer diameter: $\varnothing 0.95 \pm 0.10$ mm
 Thickness: 0.23 mm minimum average
 Style: UL 1061

Outer jacket

Material: PVC, 80 °C
 Color: white
 Diameter: $\varnothing 3.45 \pm 0.20$ mm
 Thickness: 0.76 mm minimum average


Wire marking: E339579 UL AWM STYLE 2464 28AWG 80°C
 300V VW-1 --- cUL AWM I A 80°C 300V FT1 TENSILITY

Tests

Tensile strength: 1.05 kgf/mm²
 After aging at 113 ± 2 °C for 7 days:
 Minimum tensile strength 70 % original
 Minimum elongation 65 % original
 Flexibility: no observed cracking
 Heat shock: 121 ± 1 °C / 1 hour, no observed degradation
 Deformation: 121 ± 1 °C / 1hour, ≤ 50 %
 Cold bend: -10 ± 2 °C / 1 hour, no observed cracking
 Dielectric: 2000 Vac for 1 minute without breakdown

Use:

Internal wiring or external interconnection of electronic equipment



REVISION	DATE	DESCRIPTION	PREPARED:	NOTES	TENSILITY 20802 Sockeye Place #130 Bend, OR 97701 USA tel 541.323.3228 fax 541.323.4202 800 877.670.7118 www.tensility.com		
A	1/22/2016	Initial release		RoHS and REACH compliant			
			VERIFIED:	Function test: no open, no short circuit, no intermittent	A	30-00699	
			DIMENSIONS ARE IN MILLIMETERS	Meets UL appliance wiring standard 758	SCALE: 12:1	SHEET 1 OF 1	
			TOLERANCES: X: ± 0.5 mm X.X: ± 0.3 mm X.XX: ± 0.05 mm	DESCRIPTION: Wire, 2C TS, 28 AWG, UL2464, 300V, 80C, 3.45 mm, VW-1, PVC, white			